

STYLE: C10404P
11.5 oz. Pool Cover
Vinyl Coated Polyester

TYPICAL PERFORMANCE PROPERTIES

Total Weight

ASTM D-751 11.5 oz. / yd.²

Grab Tensile

ASTM D-751 425 x 375 lbs.

Strip Tensile

ASTM D-751 300 x 200 lbs. / in.
 Procedure B

Tongue Tear

ASTM D-751 120 x 90 lbs.
 8x10 Specimen @ 12 in. / min.

Trap Tear

ASTM D-751 40 x 55 lbs.

Adhesion

ASTM D-751 10 lbs. / in.
 RF Weld

Puncture Resistance

ASTM D-4833 230 lbs.

Hydrostatic Resistance

ASTM D-751 600 psi
 Procedure A

Low Temperature

ASTM D-2136 - 55° F

Abrasion Resistance

ASTM D-3384	Face Side	300 cycles
H18, 1000 gram load	Back Side	30 cycles

Mildew Resistance

ASTM G-21 No Growth

UV Resistance

ASTM G-53 1200 Hours

Date Issued: September 6, 2010

We believe this information is the best currently available, but assume no obligation or liability in connection therewith. We make no guarantee of results and no representation that the material is fit for any particular purpose. There are NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY, unless specified in writing and signed by BondCote Corporation

P: 540.980.4461 | 800.255.9338 | F: 540.980.4466
 P.O. Box 729, 509 Burgis Avenue, Pulaski, VA 24301
 www.bondcote.com ISO 9001: 2008 Certified