

STYLE: C13604
Vinyl Laminated Polyester
Pool Cover

TYPICAL PERFORMANCE PROPERTIES

Total Weight

ASTM D-751 13 oz. / yd.²

Grab Tensile

ASTM D-751 230 x 220 lbs.

Strip Tensile

ASTM D-751 155 x 130 lbs. / in.
 Procedure B

Tongue Tear

ASTM D-751 70 x 70 lbs.
 8x10 Specimen @ 12 in. / min.

Trap Tear

ASTM D-751 50 x 40 lbs.

Adhesion

ASTM D-751 15 lbs. / in.
 RF Weld

Puncture Resistance

ASTM D-4833 80 lbs.

Hydrostatic Resistance

ASTM D-751 320 psi
 Procedure A

Low Temperature

ASTM D-2136 - 40° F

Mildew Resistance

ASTM G-21 No Growth

UV Resistance

ASTM G-53 1200 Hours

Date Issued: September 6, 2010

We believe this information is the best currently available, but assume no obligation or liability in connection therewith. We make no guarantee of results and no representation that the material is fit for any particular purpose. There are NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY, unless specified in writing and signed by BondCote Corporation

P: 540.980.4461 | 800.255.9338 | F: 540.980.4466
 P.O. Box 729, 509 Burgis Avenue, Pulaski, VA 24301
 www.bondcote.com ISO 9001: 2008 Certified