



A Heytex group company

STYLE: C22401
Super 22
Vinyl Coated Polyester

TYPICAL PERFORMANCE PROPERTIES

Total Weight

ASTM D-751 22 oz. / yd.²

Grab Tensile

ASTM D-751 510 x 570 lbs.

Strip Tensile

ASTM D-751 375 x 370 lbs. / in.
Procedure B

Tongue Tear

ASTM D-751 110 x 110 lbs.
8x10 Specimen @ 12 in. / min.

Trap Tear

ASTM D-751 45 x 50 lbs.

Adhesion

ASTM D-751 10 lbs. / in.
RF Weld

Puncture Resistance

ASTM D-4833 225 lbs.

Hydrostatic Resistance

ASTM D-751 750 psi
Procedure A

Low Temperature

ASTM D-2136 -40° F

Date Issued: September 29, 2010

We believe this information is the best currently available, but assume no obligation or liability in connection therewith. We make no guarantee of results and no representation that the material is fit for any particular purpose. There are NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY, unless specified in writing and signed by BondCote Corporation

P: 540.980.4461 | 800.255.9338 | F: 540.980.4466
P.O. Box 729, 509 Burgis Avenue, Pulaski, VA 24301
www.bondcote.com ISO 9001: 2008 Certified