

STYLE: G35445
High Tear Dock Seal
Vinyl Coated Polyester

TYPICAL PERFORMANCE PROPERTIES

<u>Total Weight</u> ASTM D-751	35 oz. / yd. ²
<u>Grab Tensile</u> ASTM D-751	645 x 675 lbs.
<u>Strip Tensile</u> ASTM D-751 Procedure B	430 x 380 lbs. / in.
<u>Tongue Tear</u> ASTM D-751 8x10 Specimen @ 12 in. / min.	175 x 175 lbs.
<u>Adhesion</u> ASTM D-751 RF Weld	10 lbs. / in.+
<u>Puncture Resistance</u> ASTM D-4833	300 lbs.
<u>Hydrostatic Resistance</u> ASTM D-751 Procedure A	1000 + psi
<u>Low Temperature</u> ASTM D-2136	- 40° F
<u>Abrasion Resistance</u> ASTM D-3384 H22, 1000 gram load	8,000 cycles
<u>Mildew Resistance</u> ASTM G-21	No Growth
<u>UV Resistance</u> ASTM G-53	1200 Hours

Date Issued: September 6, 2010

We believe this information is the best currently available, but assume no obligation or liability in connection therewith. We make no guarantee of results and no representation that the material is fit for any particular purpose. There are NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY, unless specified in writing and signed by BondCote Corporation

P: 540.980.4461 | 800.255.9338 | F: 540.980.4466
P.O. Box 729, 509 Burgis Avenue, Pulaski, VA 24301
www.bondcote.com ISO 9001: 2008 Certified