



A Heytex group company

STYLE: K70443
Vinyl Coated Polyester
Flourescent

TYPICAL PERFORMANCE PROPERTIES

Total Weight

ASTM D-751 7 oz. / yd.²

Grab Tensile

ASTM D-751 200 x 140 lbs.

Strip Tensile

ASTM D-751 145 x 80 lbs. / in.
Procedure B

Puncture Resistance

ASTM D-4833 50 lbs.

Hydrostatic Resistance

ASTM D-751 230 psi
Procedure A

Low Temperature

ASTM D-2136 - 40° F

Date Issued: September 6, 2010

We believe this information is the best currently available, but assume no obligation or liability in connection therewith. We make no guarantee of results and no representation that the material is fit for any particular purpose. There are NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY, unless specified in writing and signed by BondCote Corporation

P: 540.980.4461 | 800.255.9338 | F: 540.980.4466
P.O. Box 729, 509 Burgis Avenue, Pulaski, VA 24301
www.bondcote.com ISO 9001: 2008 Certified