

T18560
Commercial Tent
 Coated, Acrylic Topcoat, F.R., 1000 Denier Polyester

PERFORMANCE METHODS	STANDARD	METRIC
<u>Total Weight</u> ASTM D 3776, Method C	18.6 oz. / sq. yd.	630 g/m ²
<u>Grab Tensile</u> ASTM D 5034	403 x 407 lbs.	1792 x 1810 N
<u>Strip Tensile</u> ASTM D 5035	266 x 221 lbs.	1183 x 983 N
<u>Tongue Tear</u> ASTM D 2261	56 X 46 lbs.	249 X 204 N
<u>Puncture</u> ASTM D 751	205 lbs.	911 N
<u>Adhesion</u> ASTM D 751, 1" (2.54 cm) Dielectric Weld, (RF)	11.7 lbs. / in.	52 N
<u>Mullen Hydrostatic Resistance</u> ASTM D 751 Procedure A, Procedure 1	600 psi	4136 kPa
<u>Flame Resistance</u> California Fire Marshall, Title 19	6 inch max. 4 sec. max.	15.2 cm. max. 4 sec. max.
<u>Cold Crack</u> ASTM D 2136 @ -55 Degree F.	No Cracking	No Cracking
<u>Wicking</u> ASTM D 751	Pass	Pass

We believe this information is the best currently available, but assume no obligation or liability in connection therewith. We make no guarantee of results and no representation that the material is fit for any particular purpose. There are NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY, unless specified in writing and signed by BondCote Corporation

P: 540.980.4461 | 800.255.9338 | F: 540.980.4466
 P.O. Box 729, 509 Burgis Avenue, Pulaski, VA 24301
 www.bondcote.com ISO 9001: 2000 Certified