

T22560
Commercial Tent
 Coated, Acrylic Topcoat, F.R., 1000 Denier Polyester

| PERFORMANCE METHODS | STANDARD | METRIC |
|--|----------------------------|------------------------------|
| <u>Total Weight</u> ASTM D 3776, Method C | 22.1 oz. / sq. yd. | 749 g/m ² |
| <u>Grab Tensile</u> ASTM D 5034 | 400 x 400 lbs. | 1779 x 1779 N |
| <u>Strip Tensile</u> ASTM D 5035 | 250 x 220 lbs. | 1112 x 977 N |
| <u>Tongue Tear</u> ASTM D 2261 | 56 X 46 lbs. | 249 X 204 N |
| <u>Puncture</u> ASTM D 751 | 210 lbs. | 934 N |
| <u>Adhesion</u> ASTM D 751, 1" (2.54 cm) Dielectric Weld, (RF) | 11.7 lbs. / in. | 52 N |
| <u>Mullen Hydrostatic Resistance</u> ASTM D 751 Procedure A, Procedure 1 | 600 psi | 4136 kPa |
| <u>Flame Resistance</u> California Fire Marshall, Title 19 | 6 inch max. 4 sec. max. | 15.2 cm. max. 4 sec. max. |
| <u>Cold Crack</u> ASTM D 2136 @ -55 Degree F. | No Cracking | No Cracking |
| <u>Wicking</u> ASTM D 751 | Pass | Pass |

We believe this information is the best currently available, but assume no obligation or liability in connection therewith. We make no guarantee of results and no representation that the material is fit for any particular purpose. There are NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY, unless specified in writing and signed by BondCote Corporation

P: 540.980.4461 | 800.255.9338 | F: 540.980.4466
 P.O. Box 729, 509 Burgis Avenue, Pulaski, VA 24301
www.bondcote.com ISO 9001: 2008 Certified and ISO 14000 Compliant